


TEMPERATURE-TABLE for PTCR

Higher quality products and lower costs through improved, reliable firing control

Type PTCR - HTH	:	4322 020 07091	Ring Colour	:	White
Ferro no.	:	1007160	Dimensions	:	± 20 x 10 x 7,0 mm
Temperature Range °C	:	1450 - 1750°C			

Ring dia-meter mm	Ring tempe-rature °C	Ring dia-meter mm	Ring tempe-rature °C	Ring dia-meter mm	Ring tempe-rature °C	Ring dia-meter mm	Ring tempe-rature °C	Ring dia-meter mm	Ring tempe-rature °C	Ring dia-meter mm	Ring tempe-rature °C
		17,70	1706 °	18,20	1672 °	18,70	1641 °	19,20	1585 °	19,70	1466 °
		17,71	1705 °	18,21	1671 °	18,71	1641 °	19,21	1583 °	19,71	1463 °
		17,72	1704 °	18,22	1671 °	18,72	1640 °	19,22	1581 °	19,72	1459 °
		17,73	1703 °	18,23	1670 °	18,73	1639 °	19,23	1580 °	19,73	1456 °
		17,74	1702 °	18,24	1670 °	18,74	1638 °	19,24	1578 °	19,74	1453 °
		17,75	1701 °	18,25	1669 °	18,75	1638 °	19,25	1576 °	19,75	1449 °
		17,76	1701 °	18,26	1669 °	18,76	1637 °	19,26	1575 °		
		17,77	1700 °	18,27	1668 °	18,77	1636 °	19,27	1573 °		
		17,78	1699 °	18,28	1667 °	18,78	1635 °	19,28	1571 °		
		17,79	1698 °	18,29	1667 °	18,79	1634 °	19,29	1569 °		
		17,80	1697 °	18,30	1666 °	18,80	1633 °	19,30	1567 °		
17,31	1750 °	17,81	1697 °	18,31	1666 °	18,81	1632 °	19,31	1565 °		
17,32	1749 °	17,82	1696 °	18,32	1665 °	18,82	1631 °	19,32	1563 °		
17,33	1747 °	17,83	1695 °	18,33	1665 °	18,83	1631 °	19,33	1561 °		
17,34	1746 °	17,84	1694 °	18,34	1664 °	18,84	1630 °	19,34	1559 °		
17,35	1745 °	17,85	1694 °	18,35	1664 °	18,85	1629 °	19,35	1557 °		
17,36	1743 °	17,86	1693 °	18,36	1663 °	18,86	1628 °	19,36	1555 °		
17,37	1742 °	17,87	1692 °	18,37	1663 °	18,87	1627 °	19,37	1553 °		
17,38	1741 °	17,88	1692 °	18,38	1662 °	18,88	1626 °	19,38	1551 °		
17,39	1739 °	17,89	1691 °	18,39	1661 °	18,89	1625 °	19,39	1549 °		
17,40	1738 °	17,90	1690 °	18,40	1661 °	18,90	1624 °	19,40	1547 °		
17,41	1737 °	17,91	1689 °	18,41	1660 °	18,91	1623 °	19,41	1545 °		
17,42	1735 °	17,92	1689 °	18,42	1660 °	18,92	1622 °	19,42	1542 °		
17,43	1734 °	17,93	1688 °	18,43	1659 °	18,93	1621 °	19,43	1540 °		
17,44	1733 °	17,94	1687 °	18,44	1659 °	18,94	1620 °	19,44	1538 °		
17,45	1732 °	17,95	1687 °	18,45	1658 °	18,95	1618 °	19,45	1536 °		
17,46	1730 °	17,96	1686 °	18,46	1657 °	18,96	1617 °	19,46	1533 °		
17,47	1729 °	17,97	1685 °	18,47	1657 °	18,97	1616 °	19,47	1531 °		
17,48	1728 °	17,98	1685 °	18,48	1656 °	18,98	1615 °	19,48	1528 °		
17,49	1727 °	17,99	1684 °	18,49	1656 °	18,99	1614 °	19,49	1526 °		
17,50	1726 °	18,00	1684 °	18,50	1655 °	19,00	1613 °	19,50	1523 °		
17,51	1725 °	18,01	1683 °	18,51	1654 °	19,01	1612 °	19,51	1521 °		
17,52	1724 °	18,02	1682 °	18,52	1654 °	19,02	1610 °	19,52	1518 °		
17,53	1722 °	18,03	1682 °	18,53	1653 °	19,03	1609 °	19,53	1516 °		
17,54	1721 °	18,04	1681 °	18,54	1653 °	19,04	1608 °	19,54	1513 °		
17,55	1720 °	18,05	1680 °	18,55	1652 °	19,05	1607 °	19,55	1510 °		
17,56	1719 °	18,06	1680 °	18,56	1651 °	19,06	1605 °	19,56	1508 °		
17,57	1718 °	18,07	1679 °	18,57	1651 °	19,07	1604 °	19,57	1505 °		
17,58	1717 °	18,08	1679 °	18,58	1650 °	19,08	1603 °	19,58	1502 °		
17,59	1716 °	18,09	1678 °	18,59	1649 °	19,09	1601 °	19,59	1499 °		
17,60	1715 °	18,10	1678 °	18,60	1649 °	19,10	1600 °	19,60	1497 °		
17,61	1714 °	18,11	1677 °	18,61	1648 °	19,11	1599 °	19,61	1494 °		
17,62	1713 °	18,12	1676 °	18,62	1647 °	19,12	1597 °	19,62	1491 °		
17,63	1712 °	18,13	1676 °	18,63	1647 °	19,13	1596 °	19,63	1488 °		
17,64	1711 °	18,14	1675 °	18,64	1646 °	19,14	1594 °	19,64	1486 °		
17,65	1710 °	18,15	1675 °	18,65	1645 °	19,15	1593 °	19,65	1482 °		
17,66	1709 °	18,16	1674 °	18,66	1644 °	19,16	1591 °	19,66	1479 °		
17,67	1708 °	18,17	1674 °	18,67	1644 °	19,17	1589 °	19,67	1476 °		
17,68	1708 °	18,18	1673 °	18,68	1643 °	19,18	1588 °	19,68	1472 °		
17,69	1707 °	18,19	1672 °	18,69	1642 °	19,19	1586 °	19,69	1469 °		

Powder Batch #	:	427	Batch approved	
Date:	:	19/01/2012	Quality Inspection:	

For inquiries:

Customer Service Desk

Phone : +49 69 27 116 432

Fax : +49 69 27 116 243

